

INDO-MIM PVT LTD.

#45(P), KIADB Industrial Area, Doddaballapur, Bengaluru - 561203

Phone: +91-080-22048600/636 | FAX: +91-080-27630532

Email: infopowders@indo-mim.com or infohq@indo-mim.com | Website: www.indo-mim.com

C276

C276 is a Ni-base super alloy used for its creep resistant and outstanding oxidation resistant. Its Chemical Composition corresponds to UNSN10276 for use in additive manufacturing processes. Vacuum Induction Melting - Inert Gas Atomization process is used at INDO-MIM for manufacturing of powder. Our unique ASB technique improves powder sphericity, which enhances flowability in achieving consistent density and uniform build rates.

Particle Size Distribution

Light scattering (ASTM B822 / ISO 13320-1)				
Application	Size Range	D10%	D50%	D90%
MIM	<22µm	5.0 max	12.0 max	22.0 max
BJ	<25µm	5.5 max	13.5 max	25.0 max
LPBF	15 – 53µm	24.0 max	36.0 max	54.0 max


Chemical Composition (weight %)

Element	Range (%)
Carbon	0.01 max
Silicon	0.08 max
Manganese	1.0 max
Phosphorous	0.040 max
Sulphur	0.03 max
Chromium	14.50-16.50
Molybdenum	15.00-17.00
Vanadium	0.35 max
Cobalt	2.50 max
Tungsten	3.50-4.50
Iron	4.00-7.00
Nickel	Balance

Physical Properties

Property	g/cc	Test Method
Tap Density	4.60 min	ASTM B527
True Density	8.00 min	ASTM B923

Morphology



Customization on chemical composition & particle size can be made.

Packing with 10 / 50 / 100 kg containers & custom packing is possible.

MIM: Metal Injection Molding | BJ: Binder Jetting | LPBF: Laser Powder Bed Fusion

*Specification is only for illustrative purposes, and it varies with specific application requirements